

TEST REPORT

Applicant : Xiangze leather

Address: Shiling Town, Huadu District, Guangzhou City

The following sample(s) was/were submitted and identified on behalf of the applicant as:

Sample description : Cowboy leather

Date of Sample Received : 20 Apr 2024

Testing Perio 20 Apr 2024 — 20 Apr 2024

Test requirements: Test stripping strength test according to customer requirements

Test method:

Testing Item	TestMethod (Reference)
stripping strength	SATRA TM 410:1995



sted by: -----



Reviewed by: -----



This Test Report is issued by the Company subject to its General Conditions of Service printed overleaf or available on request and accessible at www.reachsvhc.com. Attention is drawn to the limitations of liability, indemnification and jurisdictional issues defined therein. Unless otherwise stated the results shown in the test report refer only to the sample(s) tested. This test report cannot be reproduced, except in full, without prior written permission of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this report is unlawful and offenders may be prosecuted to the fullest extent of the law.

(86-020) 36905956 (86-020) 36905956

TEST REPORT


Test Results:

Sample name	Testing Item	Test Method	Result
NBURGUNDY	stripping strength	SATRA TM 410:1995	Average Peel Strength : Longitudinal 1.85 Kg/3cm
			Average Peel Strength : Transverse 3.27 Kg/3cm

Note: :

- mg/kg = PPM
- N.D. = not detection (MDL) - MDL = method detection limit
- attached photo

Sample product image



..... This report end.....

This Test Report is issued by the Company subject to its General Conditions of Service printed overleaf or available on request and accessible at www.reachsvhc.com. Attention is drawn to the limitations of liability, indemnification and jurisdictional issues defined therein. Unless otherwise stated the results shown in the test report refer only to the sample(s) tested. This test report cannot be reproduced, except in full, without prior written permission of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this report is unlawful and offenders may be prosecuted to the fullest extent of the law.

(86-020) 36905956 (86-020) 36905956